

HIGH PERFORMANCE FLUTING

BASIS WEIGHTS:

- From 112 to 200 g/m²

PROPERTIES:

- High speed forming and bonding on corrugators
- Provides reliable impact protection “cushioning” and stacking strength
- Recycled

END USES:

- Beverages
- Consumer Durables
- Detergents
- Industrial Goods
- Processed Food



TYPICAL CHARACTERISTICS

Parameters	Unit	Standard Method	Tolerance	Target		
Grammage	g/m ²	T 410	±3%	105	112	125
Burst	KPA	T 807	±5%	245	255	285
S.C.T (CD)	KN/m	T 826	±5%	1.8	2.2	2.3
S.C.T (MD)	KN/m		±5%	3.3	3.4	3.7
C.M.T (MD)	Kgf		±5%	23	26	28
R.C.T (MD)	Kgf		±5%	16	18	22
Tensile Strength (CD)	Kgf	T 494	±5%	4.3	4.5	5.2
Tensile Strength (MD)	Kgf	T 494	±5%	9.2	9.4	11.2
Thickness	M.M		±5%	0.175	0.189	0.200
Cobb 60	g/m ²		±5%	30	30	30
Moisture Content	%	T 412	±1%	6	6	6

