

NORMAL FLUTING

BASIS WEIGHTS:

- From 112 to 200 g/m²

PROPERTIES:

- High speed forming and bonding on corrugators
- Provides reliable impact protection “cushioning” and stacking strength
- Recycled

END USES:

- Beverages
- Consumer Durables
- Detergents
- Industrial Goods
- Processed Food



TYPICAL CHARACTERISTICS

Parameters	Unit	Standard Method	Tolerance	Target			
Grammage	g/m ²	T 410	±3%	105	112	125	150
Burst	KPA	T 807	±5%	122	135	142	155
S.C.T (CD)	KN/m	T 826	±5%	1.1	1.2	1.35	1.5
S.C.T (MD)	KN/m		±5%	1.8	1.8	2	2.4
C.M.T (MD)	Kgf		±5%	10	10.5	12	14
R.C.T (MD)	Kgf		±5%	10.2	12	14.4	18
Tensile Strength (CD)	Kgf	T 494	±5%	2.3	2.6	2.9	3.3
Tensile Strength (MD)	Kgf	T 494	±5%	5.4	5.9	6.5	7.4
Thickness	M.M		±5%	0.172	0.194	0.210	0.245
Cobb 60	g/m ²		±5%	-	-	-	-
Moisture Content	%	T 412	±1%	6	6	6	7

