

HIGH PERFORMANCE TESTLINER ONE FACE

BASIS WEIGHTS:

- From 112 to 200 g/m²

PROPERTIES:

- Smooth surface providing excellent appearance, high quality printing, and water resisting properties.
- Rougher bottom surface making it easier to bond with the corrugating medium
- Recycled

END USES:

- Beverages
- Consumer Durables
- Detergents
- Industrial Goods
- Processed Food



TYPICAL CHARACTERISTICS

Parameters	Unit	Standard Method	Tolerance	Target	
Grammage	g/m ²	T 410	±3%	125	140
Burst	KPA	T 807	±5%	275	285
S.C.T (CD)	KN/m	T 826	±5%	2.2	2.4
S.C.T (MD)	KN/m		±5%	3.4	3.8
C.M.T (MD)	Kgf		±5%	27	30
R.C.T (MD)	Kgf		±5%	22.6	27
Tensile Strength (CD)	Kgf	T 494	±5%	5	5.4
Tensile Strength (MD)	Kgf	T 494	±5%	10.4	11.2
Thickness	M.M		±5%	0.200	0.235
Cobb 60	g/m ²		±5%	30	30
Moisture Content	%	T 412	±1%	6	6

