

HIGH PERFORMANCE TESTLINER TWO FACE

BASIS WEIGHTS:

- From 112 to 200 g/m²

PROPERTIES:

- Smooth surface providing excellent appearance, high quality printing, and water resisting properties.
- Rougher bottom surface making it easier to bond with the corrugating medium
- Recycled

END USES:

- Beverages
- Consumer Durables
- Detergents
- Industrial Goods
- Processed Food



TYPICAL CHARACTERISTICS						
Parameters	Unit	Standard Method	Tolerance	Target		
Grammage	g/m ²	T 410	±3%	125	140	150
Burst	KPA	T 807	±5%	300	310	320
S.C.T (CD)	KN/m	T 826	±5%	2.4	2.6	2.9
S.C.T (MD)	KN/m		±5%	3.8	4.2	4.5
C.M.T (MD)	Kgf		±5%	29	32	33
R.C.T (MD)	Kgf		±5%	23	25	28
Tensile Strength (CD)	Kgf	T 494	±5%	5.3	5.8	6.1
Tensile Strength (MD)	Kgf	T 494	±5%	11.5	12	12.4
Thickness	M.M		±5%	0.200	0.235	0.245
Cobb 60	g/m ²		±5%	30	30	30
Moisture Content	%	T 412	±1%	6	6	6

