

NORMAL TESTLINER

BASIS WEIGHTS:

- From 112 to 200 g/m²

PROPERTIES:

- Smooth surface providing excellent appearance, high quality printing, and water resisting properties.
- Rougher bottom surface making it easier to bond with the corrugating medium
- Recycled

END USES:

- Beverages
- Consumer Durables
- Detergents
- Industrial Goods
- Processed Food



TYPICAL CHARACTERISTICS

Parameters	Unit	Standard Method	Tolerance	Target	
Grammage	g/m ²	T 410	±3%	125	140
Burst	KPA	T 807	±5%	190	200
S.C.T (CD)	KN/m	T 826	±5%	1.7	1.9
S.C.T (MD)	KN/m		±5%	2.5	2.7
C.M.T (MD)	Kgf		±5%	18	22
R.C.T (MD)	Kgf		±5%	20	22
Tensile Strength (CD)	Kgf	T 494	±5%	3.5	3.6
Tensile Strength (MD)	Kgf	T 494	±5%	8.5	8.3
Thickness	M.M		±5%	0.205	0.225
Cobb 60	g/m ²		±5%	-	-
Moisture Content	%	T 412	±1%	6	6

